



THERMAFIBER® RAINBARRIER® CI HIGH COMPRESSIVE MAX (140) MINERAL WOOL INSULATION

Thermafiber® RainBarrier® ci High Compressive Max (140) continuous insulation boards are designed to support cladding attachment with minimal penetrations. The use of ThermaCrimp™ technology allows for superior compressive strength while providing thermal efficiency, non-combustibility, water repellency, and flexibility when working with uneven substrates. RainBarrier® ci High Compressive Max can be used behind heavy-weight cladding types – including combustible and open-joint assemblies.

Features

- High compressive strength to support cladding attachment system with minimal penetration through continuous insulation
- Vapor permeable
- Non-combustible and non-deteriorating
- Helps conserve energy/reduce greenhouse gas emissions
- Fire-resistant to temperatures above 2,000°F (1,093°C)
- Enhances acoustical performance
- Minimum 70% recycled content¹
- Contributes to credits in several green building programs, such as LEED® and Green Globes®

Standards, Codes Compliance

- ASTM C612, Mineral Fiber Block and Board Thermal Insulation, Types IA, IB, II, III, IVA, IVB

Technical Data

TESTED TO ASTM C518

Thickness	Nominal Density	"k" @ 75° [24°C] BTU.in/hr. sq. ft. °F	"R" value per inch of thickness ²
1"-4"	14.0 pcf	0.24	4.2

² R = thickness divided by "k."

Acoustical Performance

	THICKNESS	125 HZ	250 HZ	500 HZ	1000 HZ	2000 HZ	4000 HZ	NRC
ASTM C423	1"	0.10	0.41	0.86	0.97	0.96	0.96	0.80
	2"	0.33	0.79	0.77	0.93	0.93	0.94	0.85
	4"	0.44	0.69	0.89	0.90	0.93	0.95	0.85

Physical Properties

PROPERTY	TEST METHOD	VALUE
Compressive Strength	ASTM C165	1,296 lbs/ft ² @ 10% deformation
Corrosion of Steel, Aluminum, and Copper	ASTM C665	Pass
Combustibility	ASTM E136	Non-combustible
Water Vapor Permeance	ASTM E96	57 perm
Water Vapor Sorption	ASTM C1104	Sorption < 0.1% by volume
Linear Shrinkage	ASTM C356	<2% @ 1,200°F (650°C)
Surface Burning Characteristics	ASTM E84	Flame Spread 0, Smoke Developed 0
Fungi-Resistance	ASTM C1338	Complies
Odor	ASTM C1304	Complies
Chemical analysis for Cl, Fl, Na+, SiO ₄ ⁴	ASTM C871/ ASTM C795	Results fall within acceptability limits of ASTM C795

Availability

PRODUCT	AVAILABLE THICKNESS IN ½" INCREMENTS	STANDARD DIMENSIONS ^{3,4}
RainBarrier® ci HC Max	1"-4"	24" x 48", 48" x 72"
Tolerances	+1/8", -1/16"	Width: ±1/8", Length: ±1/4"

³ See our product guide for more details.

⁴ Custom sizes are available upon request.

Installation

Thermafiber, Inc. recommends mechanical attachment of Thermafiber® RainBarrier® insulation products. See Owens Corning publication “Thermafiber® RainBarrier® Continuous Insulation Guide” (Pub. No. 10021356) for more information.

Product Options

Recycled Content Options^{1,5}:

- EPA Choice Fiber (U.S. Government Buildings)Minimum 75%
- Standard Fiber70%

5 Recycled content options other than standard must be specified at time of order.

Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation, and composite solutions, delivering a broad range of high-quality products and services.

Owens Corning is committed to driving sustainability by delivering solutions, transforming markets, and enhancing lives. More information can be found at www.owenscorning.com.

Certifications and Sustainable Features

- ¹Verified by ICC-ES to contain a minimum of 70% recycled content. See ICC-ES Evaluation Report VAR-1025 at icc-es.org.
- Environmental Product Declaration (EPD) has been certified by UL Environment. For more information, visit ul.com/epd.
- Rainbarrier® products have a published Health Product Declaration (HPD).



Declare.



Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for, the accuracy or reliability of data associated with particular uses of any product described herein. Owens Corning reserves the right to modify this document without prior notice.

Green Globes® is a registered trademark of Green Building Initiative, Inc.

UL® and the UL® logo are trademarks of UL LLC.

Notes

For additional information, refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

THERMAFIBER, INC.
ONE OWENS CORNING PARKWAY
TOLEDO, OH 43659 USA

888-TFIBER1 [834-2371]
www.owenscorning.com/thermafiber

Pub. No. 10023500-D. Printed in U.S.A. May 2024.
© 2024 Owens Corning. All Rights Reserved.